



Modiran Trading Company
www.irxp.com – info@irxp.com
 +98 21 8861 7337 – 9
 +98 912 149 6126

JEY Refinery Bitumen Analysis	A: 60/70	B: 85/100	TEST METHOD
PENETRATION@ 25 DEG.C	60/70	85/100	D.5
SOFTENING POINT DEG.C	49/56	45/62	D.36
DUCTILITY@ 25 DEG.C	100 MIN	100 MIN	D. 113
LOSS ON HEATING %WT	0.2 MAX	0.5 MAX	D.6
FLASH POINT DEG.C	250 MIN	225 MIN	D.92
SOLUBILITY IN C52 % WT	99.05 MIN	99.05 MIN	D.4
Spot Test	Negative	Negative	A.A.S.H.O.T.102
DROP IN PENETRATION AFTER HEATING	20 MAX	20 MAX	D.5
DENSITY@25 DEG.C	1.01/1.06	1.001/1.05	D.70 D.3289